

THE INSTITUTE OF PAPER CHEMISTRY, APPLETON, WISCONSIN

CONTINUOUS BASE-LINE STUDY (MODIFIED)
(MILL CORRUGATING MEDIUM DATA FOR APRIL, MAY, JUNE, 1985)

Project 2694-2

Report Sixty

A Progress Report

to

FOURDRINIER KRAFT BOARD GROUP

OF THE

AMERICAN PAPER INSTITUTE

September 1, 1985

BASE-LINE
2nd QUARTER, 1985

THE INSTITUTE OF PAPER CHEMISTRY

Appleton, Wisconsin

CONTINUOUS BASE-LINE STUDY (MODIFIED)
(MILL CORRUGATING MEDIUM DATA FOR APRIL, MAY, JUNE, 1985)

Project 2694-2

Report Sixty

A Progress Report

to

FOURDRINIER KRAFT BOARD GROUP

OF THE

AMERICAN PAPER INSTITUTE

September 1, 1985

TABLE OF CONTENTS

	Page
SUMMARY	1
INTRODUCTION	2
PRESENTATION OF DATA	2
Presentations (Tables):	
Tables I-II-III-IV. 26-Lb Corrugating Medium, Monthly Averages of Mill Data	3-4-5-6
Table V. Data on Conditioning and Testing Environments	7
APPENDIX. NOTES A, B, C, D, AND E USED IN TABULATION OF MILL DATA	9

THE INSTITUTE OF PAPER CHEMISTRY

Appleton, Wisconsin

CONTINUOUS BASE-LINE STUDY (MODIFIED)
(MILL CORRUGATING MEDIUM DATA FOR APRIL, MAY, JUNE, 1985)

SUMMARY OF 26-Lb CORRUGATING MEDIUM DATA
(MAR-JUN. 1985)

Test		MAR		APR		MAY		JUN	
		Total	Recycled	Total	Recycled	Total	Recycled	Total	Recycled
Moisture content, %	Max.	9.6	7.4	9.7	7.1	9.7	7.2	9.5	7.1
	Min.	4.3	4.3	4.3	4.3	4.4	4.4	4.3	4.3
	Ave.	6.6(33)	5.9(13)	6.7(34)	5.6(13)	6.6(32)	5.8(13)	6.7(33)	5.9(13)
Adj. basis weight, lb/M sq ft	Max.	27.6	27.6	27.4	27.4	27.5	27.5	27.1	27.1
	Min.	25.3	25.6	25.2	25.8	25.1	25.9	25.1	25.1
	Ave.	26.4(33)	26.6(13)	26.3(34)	26.5(13)	26.4(32)	26.6(13)	26.3(33)	26.5(13)
Caliper, pt.	Max.	11.4	11.4	11.1	11.1	10.8	10.8	10.9	10.9
	Min.	7.9	7.9	7.9	7.9	8.0	8.0	7.8	7.8
	Ave.	9.6(26)	9.3(12)	9.6(27)	9.4(12)	9.5(26)	9.4(12)	9.5(27)	9.4(12)
Concora, lb	Max.	69.1	69.1	69.2	69.2	69.3	69.3	70.0	69.6
	Min.	51.5	51.5	54.3	54.3	56.5	56.5	54.0	54.0
	Ave.	60.9(33)	59.9(13)	61.4(34)	60.6(13)	61.4(32)	60.9(13)	61.2(33)	60.5(13)
CD Ring Crush, lb	Max.	43.0	40.0	43.0	37.0	41.1	40.0	41.0	38.0
	Min.	24.0	26.0	24.2	24.2	23.2	23.2	23.2	23.2
	Ave.	31.6(25)	31.0(9)	31.0(25)	30.1(9)	32.1(25)	30.3(9)	31.5(26)	29.6(9)

Max. and Min. values are current machine averages.
Ave. value is current F.K.P.C. average, number of machines is indicated in parentheses.

INTRODUCTION

The continuous base-line study (modified) is a compilation of monthly averages of mill test data obtained routinely on 26-lb corrugating medium manufactured in the member mills of F.K.B.G. Mill data are included for moisture content, basis weight, caliper, Concora, and C.D. Ring Crush made on the production of individual machines which produced at least 500 tons of this grade weight during a given month.

PRESENTATION OF DATA

For the 26-lb grade weight of corrugating medium referred to earlier, data on conditioning and testing environments, mill test averages for moisture content, adjusted basis weight, caliper, Concora, and C.D. Ring Crush results are compiled in the following tables.

Table Number	Description
I-II-III-IV	Mill Test Averages on 26-Lb Corrugating Medium
V	Data on Conditioning and Testing Environments

The procedure used in calculating cumulative machine averages, machine factors, machine indexes, and F.K.B.G. indexes are described in the Appendix.

It should be explained that the number of machines for which data are compiled in each table for a specified month varies for these reasons: a machine must have (a) produced at least 500 tons of 26-lb corrugating medium during the specified month, or (b) produced 500 tons of 26-lb corrugating medium during any one or more of the 12 months prior to the specified month (so that a cumulative average is available), to be included in a given table.

TABLE I

AVERAGES OF ROUTINE MILL QUALITY CONTROL DATA FOR 26 LB. CORRUGATING MEDIUM

APRIL, 1985

	MOISTURE CONTENT, PERCENT				ADJ. BASIS WT.,*A LB./ M SQ. FT.				CALIPER, PT.				CONCORA TEST LB.			
	MACHINE DATA				MACHINE DATA				MACHINE DATA				MACHINE DATA			
CODE *E	CUR. AV.	CUM. AV.	FACT. *B	IND. *C	CUR. AV.	CUM. AV.	FACT. *B	IND. *C	CUR. AV.	CUM. AV.	FACT. *B	IND. *C	CUR. AV.	CUM. AV.	FACT. *B	IND. *C
A1	7.8	7.8	100.0	118.2	26.0	26.1	99.6	98.5					61.0	58.2	104.8	100.2
C1	6.5	6.7	97.0	96.5	26.2	26.2	100.0	99.2	9.7	9.6	101.0	101.0	64.0	63.2	101.3	105.1
D1(R)	5.7	5.8	98.3	86.4	26.6	26.6	100.0	100.8	10.5	9.7	108.2	109.4	61.6	60.4	102.0	101.1
I1(R)	5.8	5.8	100.0	87.9	26.8	26.6	100.8	101.5	10.5	10.4	101.0	109.4	61.3	60.9	100.6	100.6
J1	7.2	6.8	105.9	109.1	26.3	26.4	99.6	99.6	8.8	8.7	101.1	91.7	68.0	68.2	99.7	111.6
L1(R)	7.1	7.3	97.3	107.6	26.3	26.3	100.0	99.6					61.0	61.8	98.7	100.2
O1	5.8	6.0	96.7	87.9	26.7	26.8	99.6	101.1					58.0	59.0	98.3	95.2
P1	6.4	6.6	97.0	97.0	26.6	26.4	100.8	100.8	9.4	9.9	94.9	97.9	63.0	63.4	99.4	103.4
Q1	7.5	7.4	101.4	113.6	26.4	26.5	99.6	100.0	10.2	10.2	100.0	106.2	58.0	57.7	100.5	95.2
D2	8.9	8.6	103.5	134.8	25.7	25.9	99.2	97.3	10.8	10.5	102.8	112.5	61.6	61.4	100.3	101.1
F2	7.4	7.3	101.4	112.1	26.4	26.6	99.2	100.0	10.1	10.1	100.0	105.2	57.0	56.9	100.2	93.6
G2(R)	5.6	5.3	105.7	84.8	26.6	26.8	99.2	100.8	7.9	7.8	101.3	82.3	60.1	59.4	101.2	98.7
H2(R)	7.0	7.0	100.0	106.1	26.3	26.4	99.6	99.6	9.3	9.3	100.0	96.9	69.2	69.2	100.0	113.6
K2(R)	5.8	5.8	100.0	87.9	26.3	26.3	100.0	99.6	9.5	9.5	100.0	99.0	62.8	63.9	98.3	103.1
L2	7.6	7.3	106.8	118.2	26.1	26.3	99.2	98.9					62.0	59.8	103.7	101.8
Q2	7.0	7.2	97.2	106.1	26.2	26.1	100.4	99.2	8.5	10.1	84.2	88.5	61.0	61.5	99.2	100.2
R2	6.8	6.8	100.0	103.0	26.8	26.9	99.6	101.5		9.0			63.9	63.9	100.0	104.9
S2	6.9	6.9	100.0	104.5	26.2	26.2	100.0	99.2					61.0	62.2	98.1	100.2
V2	6.6	6.6	100.0	100.0	26.5	26.4	100.4	100.4	9.0	9.2	97.8	93.8	63.0	61.5	102.4	103.4
Y2(R)	4.3	4.4	97.7	65.2	27.4	27.4	100.0	103.8	9.0	9.0	100.0	93.8	55.2	52.0	106.2	90.6
Z2(R)	6.0	6.0	100.0	90.9	26.6	26.6	100.0	100.8	9.0	9.0	100.0	93.8	54.3	51.6	105.2	89.2
A3	7.2	6.3	114.3	109.1	26.1	26.1	100.0	98.9	8.7	8.7	100.0	90.6	69.0	67.0	103.0	113.3
I3(R)	6.0	6.0	100.0	90.9	25.8	26.0	99.2	97.7	8.9	8.8	101.1	92.7	55.0	56.0	98.2	90.3
K3(R)	6.0	6.1	98.4	90.9	26.5	26.6	99.6	100.4	8.8	9.0	97.8	91.7	63.0	63.7	98.9	103.4
L3		6.8				26.1				7.9				70.0		
M3(R)	4.8	4.4	109.1	72.7	26.9	26.9	100.0	101.9	9.5	9.1	104.4	99.0	58.2	59.6	97.6	95.6
T3	8.7	8.7	100.0	131.8	26.0	26.0	100.0	98.5	9.7	9.2	105.4	101.0	61.0	61.5	99.2	100.2
W3	9.7	9.6	101.0	147.0	25.2	25.3	99.6	95.4	10.0	10.0	100.0	104.2	67.7	64.0	105.8	111.2
D4	6.9	6.8	101.5	104.5	26.4	26.4	100.0	100.0	9.4	9.8	95.9	97.9	61.0	59.8	102.0	100.2
D4(R)	4.6	4.3	107.0	69.7	26.9	27.0	99.6	101.9	9.2	9.3	98.9	95.8	60.4	59.6	101.3	99.2
P4	6.0	6.0	100.0	90.9	25.9	25.8	100.4	98.1	9.7	9.5	102.1	101.0	60.8	61.0	99.7	99.8
Q4	7.1	7.1	100.0	107.6	26.3	26.4	99.6	99.6	10.7	10.7	100.0	111.4	59.5	59.8	99.5	97.7
R4	7.1	7.2	98.6	107.6	26.1	26.1	100.0	98.9					61.0	59.2	103.0	100.2
T4(R)	7.0	7.2	97.2	106.1	26.0	26.2	99.2	98.5	11.1	11.5	96.5	115.6	63.8	62.2	102.6	104.8
U4	6.5	6.3	103.2	98.5	26.1	26.2	99.6	98.9	10.2	10.0	102.0	106.2	59.0	59.9	98.5	96.9

FKBG DATA

	TOTAL	RECYCLED	TOTAL	RECYCLED	TOTAL	RECYCLED	TOTAL	RECYCLED
CUR. AV	6.7	5.8	26.3	26.5	9.6	9.4	61.4	60.4
CUM. AV	6.6	5.8	26.4	26.6	9.6	9.4	60.9	60.2
IND. *D	101.5	100.0	99.6	99.6	100.0	100.0	100.8	100.3

(*)-- NOTES A, B, C, D, AND E, ARE GIVEN IN APPENDIX.

TABLE II

AVERAGES OF ROUTINE MILL QUALITY CONTROL DATA FOR 26 LB. CORRUGATING MEDIUM

MAY, 1985

	MOISTURE CONTENT, PERCENT				ADJ. BASIS WT.,*A LB./ M SQ. FT.				CALIPER, PT.				CONCORA TEST LB.			
	MACHINE DATA				MACHINE DATA				MACHINE DATA				MACHINE DATA			
CODE *E	CUR. AV.	CUM. AV.	FACT. *B	IND. *C	CUR. AV.	CUM. AV.	FACT. *B	IND. *C	CUR. AV.	CUM. AV.	FACT. *B	IND. *C	CUR. AV.	CUM. AV.	FACT. *B	IND. *C
A1	7.4	7.9	93.7	112.1	26.2	26.1	100.4	99.2					61.0	58.8	103.7	100.0
C1	6.6	6.7	98.5	100.0	26.2	26.2	100.0	99.2	9.5	9.6	99.0	99.0	62.0	63.1	98.2	101.6
D1(R)	5.7	5.8	98.3	86.4	26.7	26.6	100.4	101.1	10.4	9.8	106.1	108.3	61.6	60.5	101.8	101.0
I1(R)	5.8	5.8	100.0	87.9	26.6	26.6	100.0	103.8	10.5	10.5	100.0	109.4	61.2	60.9	100.5	100.3
J1	6.8	6.8	100.0	103.0	26.2	26.4	99.2	99.2	8.6	8.7	98.8	89.6	67.0	68.2	98.2	109.8
L1(R)	7.2	7.3	98.6	109.1	26.4	26.3	100.4	100.0					62.3	61.8	100.8	102.1
O1	5.8	5.9	98.3	87.9	26.8	26.8	100.0	101.5					59.0	58.8	100.3	96.7
P1	6.5	6.6	98.5	98.5	26.4	26.4	100.0	100.0	9.3	9.9	93.9	96.9	62.0	63.0	98.4	101.6
Q1	7.4	7.4	100.0	112.1	26.5	26.5	100.0	100.4	10.1	10.2	99.0	105.2	59.0	57.8	102.1	96.7
O2	8.5	8.6	98.8	128.8	26.1	25.8	101.2	98.9	10.5	10.6	99.0	109.4	59.2	61.3	96.6	97.0
F2		7.3				26.5				10.0				57.0		
G2(R)	5.0	5.3	94.3	75.8	26.8	26.8	100.0	101.5	8.0	7.8	102.6	83.3	60.0	59.4	101.0	98.4
H2(R)	6.9	7.0	98.6	104.5	26.4	26.4	100.0	100.0	9.3	9.3	100.0	96.9	69.3	69.2	100.1	113.6
K2(R)	5.8	5.8	100.0	87.9	26.3	26.3	100.0	99.6	9.5	9.5	100.0	99.0	63.0	63.7	98.9	103.3
L2	7.5	7.3	102.7	113.6	26.8	26.3	101.9	101.5					63.0	60.1	104.8	103.3
Q2	7.2	7.2	100.0	109.1	26.2	26.1	100.4	99.2	8.7	9.9	87.9	90.6	62.0	61.6	100.6	101.6
R2	6.3	6.8	92.6	95.4	26.7	26.9	99.2	101.1	9.0	9.0	100.0	93.8	68.3	63.8	107.0	112.0
S2	7.0	6.9	101.4	106.1	26.2	26.2	100.0	99.2					61.0	62.2	98.1	100.0
V2	6.8	6.6	103.0	103.0	26.5	26.5	100.0	100.4	9.2	9.1	101.1	95.8	62.0	61.9	100.2	101.6
Y2(R)	4.9	4.4	111.4	74.2	27.5	27.4	100.4	104.2	9.0	9.0	100.0	93.8	56.5	52.2	108.2	92.6
Z2(R)	6.0	6.0	100.0	90.9	26.8	26.6	100.8	101.5	9.0	9.0	100.0	93.8	56.5	51.8	109.1	92.6
A3		6.4				26.1				8.7				67.2		
I3(R)	6.0	6.0	100.0	90.9	25.9	25.9	100.0	98.1	8.6	8.8	97.7	89.6	57.0	55.8	102.2	93.4
K3(R)	6.0	6.1	98.4	90.9	26.7	26.6	100.4	101.1	8.9	9.0	98.9	92.7	63.0	63.7	98.9	103.3
L3		6.8				26.1				7.9				70.0		
M3(R)	4.4	4.4	100.0	66.7	27.0	26.9	100.4	102.3	9.0	9.1	98.9	93.8	58.7	59.4	98.8	96.2
T3	8.7	8.7	100.0	131.8	26.0	26.0	100.0	98.5	9.3	9.3	100.0	96.9	62.0	61.5	100.8	101.6
W3	9.7	9.6	101.0	147.0	25.1	25.2	99.6	95.1	10.0	10.0	100.0	104.2	63.3	64.3	98.4	103.8
D4	7.0	6.8	102.9	106.1	26.1	26.4	98.9	98.9	9.3	9.7	95.9	96.9	61.0	60.0	101.7	100.0
O4(R)	5.0	4.3	116.3	75.8	26.8	27.0	99.2	101.5	9.3	9.3	100.0	96.9	58.6	59.7	98.2	96.1
P4	5.9	6.0	98.3	89.4	26.1	25.8	101.2	98.9	9.7	9.6	101.0	101.0	61.5	61.0	100.8	100.8
Q4	7.0	7.1	98.6	106.1	26.4	26.3	100.4	100.0	10.8	10.7	100.9	112.5	60.4	59.7	101.2	99.0
R4	7.0	7.1	98.6	106.1	26.2	26.1	100.4	99.2					60.0	59.4	101.0	98.4
T4(R)	7.1	7.2	98.6	107.6	26.1	26.2	99.6	98.9	10.8	11.5	93.9	112.5	63.5	62.3	101.9	104.1
U4	6.3	6.3	100.0	95.4	26.2	26.2	100.0	99.2	10.1	10.0	101.0	105.2	59.0	59.8	98.7	96.7

FKBG DATA	TOTAL	RECYCLED	TOTAL	RECYCLED	TOTAL	RECYCLED	TOTAL	RECYCLED
CUR. AV	6.6	5.8	26.4	26.6	9.5	9.4	61.4	60.9
CUM. AV	6.6	5.8	26.4	26.6	9.6	9.4	61.0	60.2
IND. *D	100.0	100.0	100.0	100.0	99.0	100.0	100.6	101.2

(*)-- NOTES A, B, C, D, AND E, ARE GIVEN IN APPENDIX.

TABLE III

AVERAGES OF ROUTINE MILL QUALITY CONTROL DATA FOR 26 LB. CORRUGATING MEDIUM

JUNE, 1985

CODE *E	MOISTURE CONTENT, PERCENT				ADJ. BASIS WT., *A LB./ M SQ. FT.				CALIPER, PT.				CONCORA TEST LB.			
	MACHINE DATA				MACHINE DATA				MACHINE DATA				MACHINE DATA			
	CUR. AV.	CUM. AV.	FACT. *B	IND. *C	CUR. AV.	CUM. AV.	FACT. *B	IND. *C	CUR. AV.	CUM. AV.	FACT. *B	IND. *C	CUR. AV.	CUM. AV.	FACT. *B	IND. *C
A1	7.6	7.8	97.4	115.2	26.1	26.1	100.0	98.9					61.0	59.3	102.9	100.0
C1	6.6	6.7	98.5	100.0	26.2	26.2	100.0	99.2	9.5	9.6	99.0	99.0	64.0	63.0	101.6	104.9
D1(R)	5.8	5.8	100.0	87.9	26.7	26.6	100.4	101.1	10.6	9.8	108.2	110.4	61.1	60.5	101.0	100.2
I1(R)	5.8	5.8	100.0	87.9	26.7	26.6	100.4	101.1	10.4	10.5	99.0	108.3	60.9	60.9	100.0	99.8
J1	7.0	6.7	104.5	106.1	25.7	26.4	97.3	97.3	8.6	8.7	98.8	89.6	70.0	68.1	102.8	114.8
L1(R)	7.1	7.2	98.6	107.6	26.3	26.3	100.0	99.6					62.0	61.8	100.3	101.6
O1	6.9	5.9	116.9	104.5	26.3	26.8	98.1	99.6					61.0	58.8	103.7	100.0
P1	6.5	6.6	98.5	98.5	26.3	26.4	99.6	99.6	9.3	9.9	93.9	96.9	61.7	62.9	98.1	101.1
Q1	7.5	7.4	101.4	113.6	26.4	26.5	99.6	100.0	10.3	10.1	102.0	107.3	58.0	57.9	100.2	95.1
D2	8.7	8.6	101.2	131.8	25.8	25.8	100.0	97.7	10.7	10.6	100.9	111.4	61.2	61.3	99.8	100.3
F2	7.5	7.3	102.7	113.6	26.4	26.5	99.6	100.0	10.1	10.0	101.0	105.2	58.0	57.1	101.6	95.1
G2(R)	5.5	5.2	105.8	83.3	26.6	26.7	99.6	100.8	7.8	7.8	100.0	81.2	59.5	59.4	100.2	97.5
H2(R)	7.0	7.0	100.0	106.1	26.4	26.4	100.0	100.0	9.2	9.3	98.9	95.8	69.6	69.2	100.6	114.1
K2(R)	5.9	5.8	101.7	89.4	26.2	26.3	99.6	99.2	9.5	9.5	100.0	99.0	63.2	63.6	99.4	103.6
L2	7.7	7.3	105.5	116.7	26.3	26.4	99.6	99.6					61.0	60.4	101.0	100.0
Q2	7.3	7.1	102.8	110.6	26.1	26.2	99.6	98.9	8.8	9.8	89.8	91.7	61.0	61.8	98.7	100.0
R2	6.3	6.8	92.6	95.4	27.0	26.9	100.4	102.3	8.9	9.0	98.9	92.7	65.8	64.1	102.6	107.9
S2	5.8	7.0	82.8	87.9	26.9	26.2	102.7	101.9					59.0	62.1	95.0	96.7
V2	6.7	6.6	101.5	101.5	26.5	26.5	100.0	100.4	9.5	9.1	104.4	99.0	61.0	61.8	98.7	100.0
Y2(R)	5.1	4.5	113.3	77.3	27.1	27.4	98.9	102.6	9.0	9.0	100.0	93.8	54.7	52.5	104.2	89.7
Z2(R)	6.0	6.0	100.0	90.9	26.6	26.6	100.0	100.8	9.0	9.0	100.0	93.8	54.0	52.1	103.6	88.5
A3		6.4				26.1				8.7				67.3		
I3(R)	6.1	6.0	101.7	92.4	25.1	26.0	96.5	95.1	8.7	8.8	98.9	90.6	58.0	56.0	103.6	95.1
K3(R)	6.0	6.1	98.4	90.9	26.6	26.6	100.0	100.8	8.8	9.0	97.8	91.7	62.0	63.5	97.6	101.6
L3		6.8				26.1				7.9				70.0		
M3(R)	4.3	4.4	97.7	65.2	27.0	26.9	100.4	102.3	9.0	9.1	98.9	93.8	59.2	59.2	100.0	97.0
T3	8.7	8.7	100.0	131.8	26.0	26.0	100.0	98.5	9.0	9.4	95.7	93.8	61.0	61.5	99.2	100.0
W3	9.5	9.6	99.0	143.9	25.2	25.2	100.0	95.4	10.0	10.0	100.0	104.2	66.1	64.2	103.0	108.4
D4	6.9	6.8	101.5	104.5	26.3	26.3	100.0	99.6	9.6	9.6	100.0	100.0	60.0	59.9	100.2	98.4
D4(R)	5.0	4.4	113.6	75.8	26.8	27.0	99.2	101.5	9.3	9.3	100.0	96.9	59.4	59.4	100.0	97.4
P4	5.8	6.0	96.7	87.9	26.3	25.8	101.9	99.6	9.6	9.6	100.0	100.0	62.9	61.1	102.9	103.1
Q4	7.2	7.1	101.4	109.1	26.3	26.4	99.6	99.6	10.9	10.7	101.9	113.5	59.8	59.7	100.2	98.0
R4	6.9	7.1	97.2	104.5	26.3	26.2	100.4	99.6					62.0	59.4	104.4	101.6
T4(R)	7.1	7.1	100.0	107.6	26.1	26.2	99.6	98.9	10.9	11.4	95.6	113.5	63.0	62.5	100.8	103.3
U4	6.2	6.3	98.4	93.9	26.1	26.2	99.6	98.9	10.0	10.1	99.0	104.2	59.0	59.7	98.8	96.7

FKBG DATA

	MOISTURE CONTENT, PERCENT		ADJ. BASIS WT., LB./ M SQ. FT.		CALIPER, PT.		CONCORA TEST LB.	
	TOTAL	RECYCLED	TOTAL	RECYCLED	TOTAL	RECYCLED	TOTAL	RECYCLED
CUR. AV	6.7	5.9	26.3	26.5	9.5	9.4	61.2	60.5
CUM. AV	6.6	5.8	26.4	26.6	9.6	9.4	61.0	60.2
IND. *D	101.5	101.7	99.6	99.6	99.0	100.0	100.3	100.5

(*)-- NOTES A, B, C, D, AND E, ARE GIVEN IN APPENDIX.

TABLE IV

AVERAGES OF ROUTINE MILL QUALITY CONTROL DATA FOR 26 LB. CORRUGATING MEDIUM

RING COMPRESSION, LBS.

	APRIL, 1985				MAY, 1985				JUNE, 1985			
	MACHINE DATA				MACHINE DATA				MACHINE DATA			
	CUR. AV.	CUM. AV.	FACT. *B	IND. *C	CUR. AV.	CUM. AV.	FACT. *B	IND. *C	CUR. AV.	CUM. AV.	FACT. *B	IND. *C
A1	28.0	28.1	99.6	90.0	27.0	28.0	96.4	86.5	28.0	28.0	100.0	89.2
C1	27.0	31.7	85.2	86.8	37.0	31.2	118.6	118.6	38.0	31.9	119.1	121.0
D1(R)												
I1(R)												
J1												
L1(R)												
O1	29.0	32.9	88.1	93.2	33.0	32.6	101.2	105.8	28.0	32.6	85.9	89.2
P1		30.3				30.2						
Q1	28.0	30.2	92.7	90.0	29.0	30.3	95.7	92.9	31.0	30.2	102.6	98.7
D2	34.8	37.2	93.5	111.9	37.1	36.8	100.8	118.9	36.3	36.8	98.6	115.6
F2	30.0	27.4	109.5	96.5		27.8			28.0	27.9	100.4	89.2
G2(R)	28.9	29.4	98.3	92.9	30.0	29.4	102.0	96.2	29.5	29.5	100.0	93.9
H2(R)												
K2(R)	32.8	30.5	107.5	105.5	32.8	30.5	107.5	105.1	32.1	30.4	105.6	102.2
L2	28.0	27.8	100.7	90.0	33.0	28.1	117.4	105.8	33.0	28.6	115.4	105.1
Q2	43.0	38.8	110.8	138.3	41.0	39.7	103.3	131.4	41.0	40.3	101.7	130.6
R2					26.0			83.3	25.0	26.0	96.2	79.6
S2	32.0	29.6	108.1	102.9	28.0	29.7	94.3	89.7	31.0	29.6	104.7	98.7
V2	34.0	34.0	100.0	109.3	36.0	34.0	105.9	115.4	37.0	34.2	108.2	117.8
Y2(R)	27.6	24.8	111.3	88.7	25.0	25.1	99.6	80.1	26.2	25.3	103.6	83.4
Z2(R)	24.2	23.2	104.3	77.8	23.2	24.0	96.7	74.4	24.7	24.6	100.4	78.7
A3												
I3(R)	37.0	39.0	94.9	119.0	40.0	38.7	103.4	128.2	38.0	39.6	96.0	121.0
K3(R)	37.0	38.1	97.1	119.0	40.0	38.1	105.0	128.2	38.0	38.3	99.2	121.0
L3												
M3(R)	24.9	26.6	93.6	80.1	24.0	26.6	90.2	76.9	23.2	26.4	87.9	73.9
T3	38.0	35.8	106.1	122.2	41.0	36.3	112.9	131.4	41.0	37.1	110.5	130.6
W3	27.1	31.6	85.8	87.1	27.8	30.9	90.0	89.1	27.9	30.5	91.5	88.8
D4		32.7				33.5				33.0		
D4(R)	27.4	25.4	107.9	88.1	25.1	26.2	95.8	80.4	24.5	26.3	93.2	78.0
P4	33.2	31.8	104.4	106.8	35.4	31.9	111.0	113.5	36.0	32.2	111.8	114.6
Q4	37.5	35.5	105.6	120.6	41.1	35.8	114.8	131.7	38.4	36.4	105.5	122.3
R4	25.0	24.4	102.4	80.4	27.0	24.2	111.6	86.5	25.0	24.5	102.0	79.6
T4(R)	31.0	27.9	111.1	99.7	33.0	28.3	116.6	105.8	30.0	28.9	103.8	95.5
U4	30.0	30.7	97.7	96.5	30.0	30.7	97.7	96.2	29.0	30.8	94.2	92.4
FKBG DATA												
	TOTAL		RECYCLED		TOTAL		RECYCLED		TOTAL		RECYCLED	
CUR. AV	31.0		30.1		32.1		30.3		31.5		29.6	
CUM. AV	31.1		29.9		31.2		30.1		31.4		30.4	
IND. *D	99.7		100.7		102.9		100.7		100.3		97.4	

(*)-- NOTES A, B, C, D, AND E, ARE GIVEN IN APPENDIX.

TABLE V

DATA ON CONDITIONING AND TESTING ENVIRONMENTS

APRIL, MAY, JUNE, 1985

	Conditioning Environment				Testing Environment
	Are Quality Samples	Procedure			Are Quality Samples Tested
Code	Conditioned Before Testing?	Time	Temp., °F	RH, %	Under Controlled Conditions of Temperature & Humidity?
A1	No	--	--	--	Yes: 73 2°F; 50 ± 2% RH
C1	No	--	--	--	Yes: 73°F; 50% RH
D1	No	--	--	--	Yes: 72 ± 4°F; 50 ± 5% RH
I1	No	--	--	--	Yes: 72 ± 4°F; 50 ± 5% RH
J1	No	--	--	--	Yes: 73 ± 2°F; 50 ± 2% RH
L1	No	--	--	--	Yes: 72 ± 2°F; 50 ± 5% RH
O1	No	--	--	--	No
P1	Yes	20 min	--	--	YesL 72 ± 2°F; 50 ± 2% RH
Q1	No	--	--	--	Yes: 72 ± 2°F; 50 ± 2% RH
P2	No	--	--	--	Yes: 72 ± 3°F; 50 ± 2% RH
F2	No	--	--	--	Yes: 72 ± 2°F; 50 ± 2% RH
G2	No	--	--	--	Yes: 75 ± 2°F; 50 ± 5% RH
H2	No	--	--		Yes: 72 ± 1°F; 50 ± 1% RH
K2	No	--	--	--	Yes: 72 ± 2°F; 50 ± 3% RH
L2	No	--	--	--	Yes: 73 ± 2°F; 50 ± 2% RH
Q2	No	--	--	--	Yes: 72 ± 2°F; 50 ± 1% RH
R2	No	--	--	--	No
S2	No	--	--	--	No
V2	No	--	--	--	No
Y2	No	--	--	--	Yes: 73 ± 3°F; 50 ± 2% RH
Z2	No	--	--	--	Yes: 73 ± 3°F; 50 ± 2% RH
A3	No	--	--	--	Yes: 73 ± 2°F; 50 ± 2% RH
I3	Yes	20 min	--	--	Yes: 72 ± 3.5°F; 50 ± 2% RH
K3	No	--	--	--	No
L3	No data was submitted for this quarter				
M3	No	--	--	--	No
T3	No	--	--	--	Yes: 70 ± 2°F; 50 ± 10% RH
W3	No	--	--	--	Yes: 72 ± 2°F; 50 ± 2% RH
D4	No	--	--	--	No
O4	No	--	--	--	No
P4	No	--	--	--	Yes: 73 ± 2°F; 50 ± 2% RH
Q4	No	--	--	--	Yes: 70 ± 2°F; 50 ± 2% RH
R4	No	--	--	--	Yes: 73 ± 2°F; 50 ± 2% RH
T4	Yes	--	--	--	Yes: 70 ± 2°F; 50 ± 2% RH
U4	No	--	--	--	No

THE INSTITUTE OF PAPER CHEMISTRY

Roger H. Van Eperen
Research Associate
Paper Materials Division

Approved by

G A Baum by WJW

Gary A. Baum
Director
Paper Materials Division

APPENDIX

NOTES A, B, C, D, AND E, USED IN TABULATIONS OF MILL DATA

Notes A, B, C, D, and E, used in the tables of mill data are given below; these notes define the procedure used in calculating adjusted basis weight, machine factor, machine index, and F.K.B.G. index. It should be stressed that each formula is applicable only to a specific physical property of corrugating medium.

Note A: Adjusted basis weight (ABW) = reported weight (RBW) adjusted to moisture content of 7.8%:

$$ABW = RBW \left[\frac{(100 - \text{reported moisture content, \%})}{(100 - 7.8)}\right]$$

Note B: Machine factor (%) $= \left[\frac{\text{Current machine average}}{\text{Cumulative machine average}}\right] \cdot 100$ where

$$\text{Cumulative machine average} = \sum \frac{\text{CMA's}^a \text{ for previous 12 months excluding CMA for current month}}{12}$$

Note C: Machine index (%) $= \left[\frac{\text{Current machine average}}{\text{Cumulative F.K.B.G. total average}}\right] \cdot 100$ where

$$\text{Cumulative F.K.B.G. average} = \sum \frac{\text{CFKBGA's}^b \text{ for previous 12 months excluding CFKBGA for current month}}{12}$$

Note D: F.K.B.G. index (%) $= \left[\frac{\text{Current F.K.B.G. average}}{\text{Cumulative F.K.B.G. average}}\right] \cdot 100$ where

$$\text{Current F.K.B.G. average} = \sum \frac{\text{CMA's}^a \text{ for current month for all machines}}{\text{Number of machines}}$$

Note E: (R) - Indicates a medium manufactured from recylced fibers.

---

[a]CMA = current machine average for a specific physical property of 26-lb corrugating medium obtained during a given month on a specific machine.

[b]CFKBGA = current F.K.B.G. average for a specific physical property of 26-lb corrugating medium obtained during a given month.